

Chemical Resistant Chart

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Chemical Name	PP	PVC	Teflon	Viton	SS 316	SS 304
Acetaldehyde	A	D	A	D	A	A
Acetamide	A	D	A	B	A	B
Acetate Solvent	B	D	A	D	A	A
Acetic Acid	B	D	A	B	B	D
Acetic Acid 20%	A	D	A	B	A	B
Acetic Acid 80%	A	C	A	B	B	D
Acetic Acid, Glacial	A	D	A	D	A	C
Acetic Anhydride	B	D	A	D	A	B
Acetone	A	D	A	D	A	A
Acetyl Bromide	N/A	D	A	N/A	N/A	N/A
Acetyl Chloride (dry)	D	C	A	A	A	A
Acetylene	A	A	A	A	A	A
Acrylonitrile	A	B	A	D	A	A
Adipic Acid	B	A	A	A	A	A
Alcohols:Amyl	B	A	A	A	A	A
Alcohols:Benzyl	A	D	A	A	B	B
Alcohols:Butyl	A	A	A	A	A	A
Alcohols:Diacetone	B	B	A	D	A	A
Alcohols:Ethyl	A	C	A	A	A	A
Alcohols:Hexyl	N/A	A	A	C	A	A
Alcohols:Isobutyl	A	A	A	A	A	A
Alcohols:Isopropyl	A	A	A	A	B	B
Alcohols:Methyl	A	A	A	C	A	A
Alcohols:Octyl	N/A	N/A	N/A	B	A	A
Alcohols:Propyl	A	A	A	A	A	A
Aluminum Chloride	A	A	A	A	B	B
Aluminum Chloride 20%	A	A	A	A	C	D
Aluminum Fluoride	A	A	A	A	D	D
Aluminum Hydroxide	A	A	A	A	C	A
Aluminum Nitrate	A	B	A	A	A	A
Aluminum Potassium Sulfate 10%	A	A	A	A	A	A
Aluminum Potassium Sulfate 100%	A	A	A	A	B	D
Aluminum Sulfate	A	A	A	A	B	B
Alums	A	N/A	A	A	A	N/A

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Amines	B	D	A	D	A	A
Ammonia 10%	A	B	A	D	A	A
Ammonia Nitrate	A	B	A	D	A	A
Ammonia, anhydrous	A	A	A	D	A	A
Ammonia, liquid	A	A	A	D	A	B
Ammonium Acetate	A	A	A	A	A	B
Ammonium Bifluoride	A	A	A	A	B	D
Ammonium Carbonate	A	A	A	A	B	B
Ammonium Caseinate	N/A	N/A	N/A	N/A	A	N/A
Ammonium Chloride	A	A	A	A	B	C
Ammonium Hydroxide	A	A	A	B	A	A
Ammonium Nitrate	A	A	A	A	A	A
Ammonium Oxalate	A	A	N/A	N/A	A	A
Ammonium Persulfate	A	A	A	A	B	A
Ammonium Phosphate, Dibasic	A	A	A	A	C	B
Ammonium Phosphate, Monobasic	A	A	A	A	C	B
Ammonium Phosphate, Tribasic	A	A	A	A	B	B
Ammonium Sulfate	A	A	A	A	B	B
Ammonium Sulfite	A	A	A	D	B	B
Ammonium Thiosulfate	N/A	N/A	N/A	N/A	A	N/A
Amyl Acetate	B	D	A	D	A	A
Amyl Alcohol	B	A	A	A	A	A
Amyl Chloride	D	D	A	B	A	A
Aniline	A	C	A	A	B	A
Aniline Hydrochloride	D	B	A	A	D	D
Antifreeze	D	A	N/A	A	A	N/A
Antimony Trichloride	A	A	A	A	D	D
Aqua Regia (80% HCl, 20% HNO ₃)	B	C	A	B	D	D
Arochlor 1248	D	N/A	A	A	B	B
Aromatic Hydrocarbons	D	D	N/A	A	C	N/A
Arsenic Acid	A	A	A	A	A	A
Arsenic Salts	N/A	A	N/A	A	N/A	N/A
Asphalt	B	A	A	A	A	B
Barium Carbonate	A	A	A	A	B	B
Barium Chloride	A	A	A	A	A	A
Barium Cyanide	D	D	A	A	A	A
Barium Hydroxide	B	A	A	A	B	B
Barium Nitrate	A	A	A	A	B	B
Barium Sulfate	B	B	A	A	B	B
Barium Sulfide	B	A	A	A	B	B
Benzaldehyde	D	D	A	D	B	B

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Benzene	D	C	A	A	B	B
Benzene Sulfonic Acid	D	A	A	A	B	B
Benzoic Acid	B	A	A	A	B	B
Benzol	B	N/A	A	A	A	A
Benzonitrile	N/A	N/A	A	N/A	D	D
Benzyl Chloride	C	N/A	N/A	A	B	C
Bleaching Liquors	A	A	A	A	N/A	N/A
Borax (Sodium Borate)	B	A	A	A	A	A
Boric Acid	A	A	A	A	A	B
Bromine	D	C	A	A	D	D
Butadiene	C	C	A	B	A	A
Butane	A	C	A	A	A	A
Butanol (Butyl Alcohol)	A	C	A	A	A	A
Butyl Amine	B	D	A	D	A	N/A
Butyl Ether	D	A	A	D	A	N/A
Butyl Phthalate	B	N/A	A	C	B	B
Butylacetate	B	D	A	D	A	B
Butylene	N/A	A	A	A	A	A
Butyric Acid	B	B	A	B	B	B
Calcium Bisulfate	N/A	N/A	N/A	N/A	A	N/A
Calcium Bisulfide	A	A	A	A	B	B
Calcium Bisulfite	A	B	A	A	A	B
Calcium Carbonate	A	A	A	A	B	A
Calcium Chlorate	N/A	B	A	A	N/A	N/A
Calcium Chloride	A	C	A	A	B	C
Calcium Hydroxide	A	B	A	A	B	B
Calcium Hypochlorite	A	B	A	A	B	C
Calcium Nitrate	A	A	A	A	B	C
Calcium Oxide	A	B	A	B	A	A
Calcium Sulfate	A	B	A	A	B	B
Calgon	A	N/A	N/A	A	A	A
Cane Juice	C	A	A	A	A	A
Carbolic Acid (Phenol)	B	D	A	A	B	B
Carbon Bisulfide	D	D	N/A	A	B	A
Carbon Dioxide (dry)	A	A	A	B	A	A
Carbon Dioxide (wet)	A	A	A	B	A	A
Carbon Disulfide	D	D	A	A	B	A
Carbon Monoxide	A	A	A	A	A	A
Carbon Tetrachloride	D	D	A	A	B	B
Carbon Tetrachloride (dry)	D	N/A	A	A	B	B
Carbon Tetrachloride (wet)	D	N/A	A	N/A	A	A

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Carbonated Water	B	A	N/A	A	A	A
Carbonic Acid	A	A	A	A	A	A
Chloric Acid	N/A	A	A	N/A	C	D
Chlorinated Glue	N/A	N/A	N/A	A	A	N/A
Chlorine (dry)	D	D	A	A	B	A
Chlorine Water	D	A	A	A	C	C
Chlorine, Anhydrous Liquid	D	D	A	A	C	C
Chloroacetic Acid	C	B	A	D	A	B
Chlorobenzene (Mono)	C	D	B	A	B	A
Chlorobromomethane	A	D	A	A	N/A	N/A
Chloroform	C	D	A	A	A	A
Chlorosulfonic Acid	D	D	A	D	B	D
Chocolate Syrup	A	N/A	A	A	A	A
Chromic Acid 10%	D	A	A	B	B	B
Chromic Acid 30%	D	A	A	A	B	B
Chromic Acid 5%	D	A	A	A	A	B
Chromic Acid 50%	D	D	A	A	B	C
Chromium Salts	N/A	A	N/A	N/A	N/A	N/A
Citric Acid	A	B	A	A	A	B
Clorox® (Bleach)	D	A	A	A	A	A
Copper Chloride	A	A	A	A	D	D
Copper Cyanide	A	A	A	A	B	B
Copper Fluoborate	N/A	A	N/A	A	D	D
Copper Nitrate	A	A	A	A	A	A
Copper Sulfate >5%	A	A	A	A	B	B
Copper Sulfate 5%	A	A	A	A	B	B
Cresols	D	D	N/A	A	A	A
Cresylic Acid	A	D	A	A	A	A
Cupric Acid	A	A	A	A	B	D
Cyanic Acid	N/A	N/A	A	A	A	A
Cyclohexane	D	D	A	A	A	A
Cyclohexanone	D	D	A	D	A	A
Detergents	A	A	A	A	A	A
Diacetone Alcohol	A	D	A	D	B	B
Dichlorobenzene	C	D	A	C	B	N/A
Dichloroethane	D	D	A	C	B	B
Diethyl Ether	A	D	A	D	B	B
Diethylamine	A	D	D	A	A	A
Diethylene Glycol	A	C	A	A	A	A
Dimethyl Aniline	D	D	A	D	B	B
Dimethyl Formamide	A	D	A	C	B	A

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Diphenyl	D	N/A	A	A	B	B
Diphenyl Oxide	D	D	A	A	A	B
Epsom Salts (Magnesium Sulfate)	A	A	A	A	B	A
Ethane	D	A	A	A	A	A
Ethanol	A	C	A	A	A	A
Ethanolamine	D	D	A	D	A	A
Ether	D	D	A	C	A	A
Ethyl Acetate	A	D	A	D	B	B
Ethyl Benzoate	B	D	A	A	N/A	N/A
Ethyl Chloride	D	D	A	A	A	A
Ethyl Ether	D	D	A	D	B	B
Ethyl Sulfate	N/A	N/A	A	A	D	D
Ethylene Bromide	D	D	A	A	A	A
Ethylene Chloride	C	D	A	B	B	B
Ethylene Chlorohydrin	D	D	A	A	B	B
Ethylene Diamine	N/A	D	A	B	B	B
Ethylene Dichloride	D	D	A	A	B	B
Ethylene Glycol	A	A	A	A	B	B
Ethylene Oxide	D	D	A	D	B	B
Fatty Acids	A	A	A	A	A	B
Ferric Chloride	A	A	A	A	D	D
Ferric Nitrate	A	A	A	A	B	B
Ferric Sulfate	A	A	A	A	A	B
Ferrous Chloride	A	A	A	A	D	D
Ferrous Sulfate	A	A	A	B	B	B
Fluoboric Acid	A	A	A	B	B	B
Fluorine	D	D	D	C	A	C
Fluosilicic Acid	A	D	A	B	B	C
Formaldehyde 100%	C	A	A	D	A	C
Formaldehyde 40%	A	A	A	A	A	A
Formic Acid	A	A	A	C	A	B
Furan Resin	D	A	A	D	A	A
Furfural	D	D	A	D	B	A
Gallic Acid	A	B	B	A	B	A
Gelatin	A	B	A	A	A	A
Glucose	A	A	A	A	A	A
Glycerin	A	A	A	A	A	A
Glycolic Acid	A	B	A	A	A	A
Gold Monocyanide	N/A	N/A	D	A	A	A
Heptane	C	C	A	A	A	A
Hexane	B	B	A	A	A	A

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Hydrazine	C	N/A	A	A	A	A
Hydrobromic Acid 100%	C	A	A	A	D	D
Hydrobromic Acid 20%	A	B	N/A	A	D	D
Hydrochloric Acid 100%	B	D	A	A	D	D
Hydrochloric Acid 20%	B	A	A	A	D	D
Hydrochloric Acid 37%	C	B	A	A	D	D
Hydrochloric Acid, Dry Gas	B	A	A	N/A	D	D
Hydrocyanic Acid	A	B	A	A	A	B
Hydrocyanic Acid (Gas 10%)	A	A	A	A	N/A	N/A
Hydrofluoric Acid 100%	C	C	A	B	B	B
Hydrofluoric Acid 20%	A	B	A	A	D	D
Hydrofluoric Acid 50%	A	B	A	B	D	D
Hydrofluoric Acid 75%	C	C	A	B	D	D
Hydrofluosilicic Acid 100%	A	B	A	A	D	D
Hydrofluosilicic Acid 20%	A	A	A	A	B	C
Hydrogen Gas	A	A	A	A	A	A
Hydrogen Peroxide 10%	A	A	A	A	B	B
Hydrogen Peroxide 100%	B	A	A	A	A	B
Hydrogen Peroxide 30%	B	A	A	A	B	B
Hydrogen Peroxide 50%	B	A	A	A	A	B
Hydrogen Sulfide (aqua)	A	B	A	D	A	C
Hydrogen Sulfide (dry)	A	A	A	D	A	C
Hydroquinone	A	B	A	B	B	B
Hydroxyacetic Acid 70%	N/A	D	A	A	N/A	N/A
Iodoform	N/A	A	C	N/A	A	A
Isooctane	A	A	A	A	A	A
Isopropyl Acetate	B	D	A	D	A	C
Isopropyl Ether	B	B	A	D	A	A
Isotane	D	A	N/A	A	N/A	N/A
Kerosene	C	D	A	A	A	A
Lacquer Thinners	D	D	A	D	A	A
Lacquers	D	D	A	D	A	A
Lactic Acid	B	B	A	A	B	B
Lead Acetate	A	B	A	D	B	B
Lead Nitrate	A	A	A	A	B	B
Lead Sulfamate	A	B	B	A	C	C
Ligroin	A	N/A	A	A	A	N/A
Lime	N/A	B	A	A	A	A
Linoleic Acid	B	A	A	B	A	B
Lithium Chloride	A	D	A	A	A	A
Lithium Hydroxide	N/A	N/A	A	N/A	B	B

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Lubricants	A	B	A	A	A	A
Lye: Ca(OH) ₂ Calcium Hydroxide	A	B	A	B	B	B
Lye: KOH Potassium Hydroxide	A	B	A	B	A	B
Lye: NaOH Sodium Hydroxide	A	A	A	B	B	B
Magnesium Bisulfate	A	A	A	N/A	A	A
Magnesium Carbonate	A	B	A	A	B	B
Magnesium Chloride	A	B	A	A	D	D
Magnesium Hydroxide	A	A	A	A	A	B
Magnesium Nitrate	A	A	A	A	B	B
Magnesium Oxide	N/A	N/A	A	C	A	A
Magnesium Sulfate (Epsom Salts)	A	A	A	A	B	A
Maleic Acid	A	A	A	A	B	A
Maleic Anhydride	D	N/A	A	A	A	A
Malic Acid	A	A	A	A	A	A
Manganese Sulfate	N/A	C	A	A	B	B
Mercuric Chloride (dilute)	B	A	A	A	D	D
Mercuric Cyanide	B	A	B	A	C	C
Mercurous Nitrate	A	A	A	A	A	A
Methane	A	B	A	A	A	A
Methanol (Methyl Alcohol)	A	A	A	C	A	A
Methyl Acetate	D	D	A	D	B	A
Methyl Acetone	N/A	D	A	D	A	A
Methyl Acrylate	D	N/A	N/A	D	N/A	A
Methyl Alcohol 10%	A	A	A	C	A	A
Methyl Bromide	C	D	A	A	A	A
Methyl Butyl Ketone	D	A	N/A	D	A	A
Methyl Cellosolve	B	D	A	D	B	B
Methyl Chloride	D	D	A	A	A	A
Methyl Dichloride	D	A	N/A	A	N/A	N/A
Methyl Ethyl Ketone	B	D	A	D	A	A
Methyl Ethyl Ketone Peroxide	N/A	N/A	N/A	D	N/A	N/A
Methyl Isobutyl Ketone	A	D	A	D	B	B
Methyl Isopropyl Ketone	N/A	D	A	D	A	A
Methyl Methacrylate	D	A	N/A	D	B	B
Methylamine	A	D	A	D	A	A
Methylene Chloride	B	D	A	B	B	B
Mineral Spirits	B	A	A	A	A	A
Monochloroacetic acid	N/A	N/A	A	C	A	A
Monoethanolamine	B	D	A	D	A	A
Morpholine	B	N/A	A	N/A	A	N/A
Naphtha	B	A	B	A	A	A

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Naphthalene	B	D	A	A	A	A
Nickel Chloride	A	A	A	A	C	D
Nickel Nitrate	A	A	A	A	B	B
Nickel Sulfate	A	A	A	A	B	B
Nitrating Acid (<15% HNO3)	C	D	A	N/A	D	C
Nitrating Acid (>15% H2SO4)	C	D	A	N/A	C	C
Nitrating Acid (Š1% Acid)	C	D	A	N/A	A	C
Nitrating Acid (Š15% H2SO4)	C	D	A	N/A	C	C
Nitric Acid (20%)	A	A	A	A	A	A
Nitric Acid (50%)	B	B	A	A	A	A
Nitric Acid (5-10%)	A	A	A	A	A	A
Nitric Acid (Concentrated)	D	B	A	A	A	A
Nitrobenzene	B	D	A	B	B	B
Nitrogen Fertilizer	N/A	N/A	A	N/A	N/A	N/A
Nitromethane	B	B	A	D	A	A
Nitrous Acid	A	A	A	B	B	B
Nitrous Oxide	D	A	A	B	B	B
Oleic Acid	B	C	A	B	A	A
Oleum 100%	D	D	A	A	A	A
Oleum 25%	D	D	A	A	B	B
Oxalic Acid (cold)	A	B	A	A	A	B
Ozone	B	B	A	A	A	B
Palmitic Acid	B	B	A	A	A	B
Paraffin	A	B	A	B	A	A
Pentane	D	A	A	A	C	C
Perchloric Acid	C	C	A	A	C	C
Perchloroethylene	D	C	A	A	A	B
Petrolatum	D	B	C	A	A	A
Phenol (10%)	B	C	A	A	B	B
Phenol (Carbolic Acid)	B	D	A	A	B	B
Phosphoric Acid (>40%)	A	B	A	A	D	D
Phosphoric Acid (crude)	B	B	A	A	B	D
Phosphoric Acid (molten)	D	D	N/A	N/A	C	N/A
Phosphoric Acid (Š40%)	A	B	A	A	C	D
Phosphoric Acid Anhydride	A	N/A	N/A	N/A	N/A	N/A
Phosphorus	A	A	A	N/A	A	A
Phosphorus Trichloride	N/A	D	A	A	A	A
Phthalic Acid	A	N/A	A	A	A	B
Phthalic Anhydride	D	D	A	A	A	A
Picric Acid	B	D	A	A	B	B
Potash (Potassium Carbonate)	A	A	N/A	A	B	B

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Potassium Bicarbonate	A	A	A	A	B	B
Potassium Bromide	A	A	A	A	B	B
Potassium Chlorate	A	A	A	A	B	B
Potassium Chloride	A	A	A	A	A	B
Potassium Chromate	A	A	A	A	B	B
Potassium Cyanide Solutions	A	A	A	A	B	B
Potassium Dichromate	A	A	A	A	B	B
Potassium Ferricyanide	A	A	A	A	B	B
Potassium Ferrocyanide	A	A	A	A	B	B
Potassium Hydroxide (Caustic Potash)	A	A	A	B	A	B
Potassium Hypochlorite	N/A	B	A	N/A	B	C
Potassium Iodide	A	A	A	A	A	A
Potassium Nitrate	A	A	A	A	B	B
Potassium Oxalate	N/A	N/A	A	N/A	B	B
Potassium Permanganate	A	A	A	A	B	B
Potassium Sulfate	A	A	A	A	A	B
Potassium Sulfide	A	A	A	A	B	B
Propylene	N/A	B	A	A	A	B
Propylene Glycol	A	C	A	A	B	B
Pyridine	A	D	A	D	A	A
Pyrogalllic Acid	A	A	A	A	B	B
Resorcinal	A	C	A	A	N/A	N/A
Rosins	A	C	A	A	A	A
Rust Inhibitors	A	N/A	N/A	A	A	A
Salicylic Acid	A	B	A	A	B	B
Salt Brine (NaCl saturated)	A	A	A	A	A	B
Sea Water	A	A	A	A	C	C
Silicone	A	A	A	A	A	A
Silver Bromide	N/A	N/A	A	N/A	D	D
Silver Nitrate	A	A	A	A	B	B
Soap Solutions	A	A	A	A	A	A
Soda Ash (see Sodium Carbonate)	A	A	A	A	A	A
Sodium Acetate	A	B	A	D	B	B
Sodium Aluminate	N/A	N/A	A	A	A	A
Sodium Benzoate	A	B	A	A	N/A	N/A
Sodium Bicarbonate	A	A	A	A	A	A
Sodium Bisulfate	A	A	A	A	C	D
Sodium Bisulfite	A	A	A	A	B	B
Sodium Borate (Borax)	A	A	A	A	B	B
Sodium Bromide	N/A	B	A	A	C	C
Sodium Carbonate	A	A	A	A	A	A

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Sodium Chlorate	A	A	A	A	B	A
Sodium Chloride	A	A	A	A	B	B
Sodium Chromate	N/A	N/A	A	A	B	B
Sodium Cyanide	A	A	A	A	B	A
Sodium Ferrocyanide	A	A	A	A	B	B
Sodium Fluoride	A	A	A	A	D	D
Sodium Hydrosulfite	N/A	C	A	A	N/A	N/A
Sodium Hydroxide (20%)	A	A	A	C	B	B
Sodium Hydroxide (50%)	A	A	A	D	B	B
Sodium Hydroxide (80%)	A	A	A	D	B	C
Sodium Hypochlorite (<20%)	A	A	A	A	C	C
Sodium Hypochlorite (100%)	B	B	A	A	D	D
Sodium Hyposulfate	N/A	N/A	A	N/A	A	A
Sodium Metaphosphate	A	A	A	A	A	A
Sodium Metasilicate	A	A	A	A	A	A
Sodium Nitrate	A	A	A	A	B	B
Sodium Perborate	A	A	A	A	B	B
Sodium Peroxide	B	B	A	A	A	A
Sodium Polyphosphate	A	A	A	A	B	B
Sodium Silicate	A	A	A	A	B	A
Sodium Sulfate	A	A	A	A	B	B
Sodium Sulfide	A	A	A	A	D	B
Sodium Sulfite	A	A	A	A	A	B
Sodium Tetraborate	N/A	A	A	A	A	A
Sodium Thiosulfate (hypo)	A	A	A	A	B	A
Stannic Chloride	A	A	A	A	D	D
Stannic Fluoborate	N/A	N/A	N/A	A	A	N/A
Stannous Chloride	A	A	A	A	A	C
Stearic Acid	A	B	A	A	A	B
Stoddard Solvent	C	C	A	A	A	A
Styrene	N/A	D	A	B	A	A
Sulfate (Liquors)	A	B	A	A	B	B
Sulfur Chloride	C	C	A	A	D	D
Sulfur Dioxide	A	A	A	A	A	D
Sulfur Dioxide (dry)	A	A	A	A	A	D
Sulfur Hexafluoride	N/A	B	N/A	N/A	N/A	N/A
Sulfur Trioxide	C	A	A	A	C	A
Sulfur Trioxide (dry)	D	A	A	A	A	D
Sulfuric Acid (<10%)	A	A	A	A	B	D
Sulfuric Acid (10-75%)	A	A	A	A	D	D
Sulfuric Acid (75-100%)	C	D	A	A	D	C

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data

Sulfuric Acid (cold concentrated)	A	D	A	B	B	C
Sulfuric Acid (hot concentrated)	D	D	A	A	C	D
Sulfurous Acid	A	A	A	A	B	B
Sulfuryl Chloride	N/A	N/A	A	N/A	N/A	N/A
Tannic Acid	A	A	A	A	A	B
Tartaric Acid	A	A	A	A	C	C
Tetrachloroethane	C	C	A	A	A	B
Tetrachloroethylene	D	D	A	A	A	N/A
Tetrahydrofuran	C	D	A	D	A	A
Toluene (Toluol)	C	D	A	C	A	A
Trichloroacetic Acid	A	B	A	C	C	D
Trichloroethane	C	C	A	A	B	B
Trichloroethylene	C	D	A	A	B	B
Trichloropropane	N/A	N/A	A	A	A	A
Tricresylphosphate	A	D	A	A	B	B
Triethylamine	D	B	A	D	A	A
Trisodium Phosphate	A	A	A	A	B	B
Turpentine	D	D	A	A	A	A
Urea	A	D	A	A	B	B
Uric Acid	N/A	A	A	N/A	B	B
Urine	A	A	A	A	A	A
Vinegar	A	B	A	A	A	A
Vinyl Acetate	B	D	A	A	B	B
Vinyl Chloride	N/A	D	A	A	A	B
Weed Killers	N/A	N/A	N/A	A	A	A
Whey	N/A	N/A	A	A	A	A
White Liquor (Pulp Mill)	A	A	A	A	A	A
White Water (Paper Mill)	A	A	N/A	A	A	A
Xylene	B	D	A	B	B	B
Zinc Chloride	A	B	A	A	B	B
Zinc Hydrosulfite	N/A	N/A	A	N/A	A	A
Zinc Sulfate	A	A	A	A	A	B

Key:

A = Excellent, B = Good, C = Fair, D = Not Recommended, N/A = No Test Data